

06/08/00

0349 U.S. PTO

06-09-00

A

Please type a plus sign (+) inside this box ☐

UTILITY PATENT APPLICATION TRANSMITTAL (Only for new nonprovisional applications under 37 C.F.R. § 1.53(b))		Attorney Docket No. 109026-0068
First Inventor or Application Identifier Joseph M. Jacobson et al.		
Title	METHODS AND APPARATUS FOR MANUFACTURING BIOELECTRONIC DEVICES	
Express Mail Label No.	EL056745053US	

APPLICATION ELEMENTS See MPEP chapter 600 concerning utility application contents		ADDRESS TO: Assistant Commissioner for Patents Box Patent Application Washington, DC 20231	
1. <input checked="" type="checkbox"/> *Fee Transmittal Form (e.g., PTO/SB/17) (Submit an original and a duplicate for fee processing)		6. <input type="checkbox"/> Microfiche Computer Program (Appendix)	
2. <input checked="" type="checkbox"/> Specification [Total Pages 24] (preferred arrangement set forth below) <ul style="list-style-type: none">- Descriptive title of the invention- Cross References to Related Applications- Statement Regarding Fed sponsored R & D- Reference to Microfiche Appendix- Background of the Invention- Brief Summary of the Invention- Brief Description of the Drawings (if filed)- Detailed Description- Claim(s)- Abstract of the Disclosure		7. Nucleotide and/or Amino Acid Sequence Sequence Submission (if applicable, all necessary) <ul style="list-style-type: none">a. <input type="checkbox"/> Computer Readable Copyb. <input type="checkbox"/> Paper Copy (Identical to computer copy)c. <input type="checkbox"/> Statement verifying identity of above copies	
3. <input checked="" type="checkbox"/> Drawing(s) [Total Sheets 4]		ACCOMPANYING APPLICATION PARTS 8. <input type="checkbox"/> Assignment Papers (cover sheet & document(s)) 37 C.F.R. § 3.73(b) 9. <input type="checkbox"/> Statement (when there is <input checked="" type="checkbox"/> Power of Attorney an assignee) 10. <input type="checkbox"/> English Translation Document (if applicable) 11. <input type="checkbox"/> Information Disclosure Statement (IDS)/PTO-1449 <input type="checkbox"/> Copies of IDS Citations 12. <input type="checkbox"/> Preliminary Amendment 13. <input checked="" type="checkbox"/> Return Receipt Postcard (MPEP 503) (Should be specifically itemized) *Small Entity 14. <input type="checkbox"/> Statement(s) <input type="checkbox"/> Statement filed in prior application, (PTO/SB/09-12) Status still proper and desired 15. <input type="checkbox"/> Certified Copy of Priority Document(s) (if foreign priority is claimed) 16. <input type="checkbox"/> Other:	
4. Oath or Declaration [Total Pages] <ul style="list-style-type: none">a. <input checked="" type="checkbox"/> Newly executed (unsigned)b. <input type="checkbox"/> Copy from a prior application (37 C.F.R. § 1.63(d)) (for continuation/divisional with Box 17 completed) (Note Box 5 below) DELETION OF INVENTOR(S) Signed statement attached deleting inventor(s) named in the prior application, see 37 C.F.R. §§ 1.63(d)(2) and 1.33(b).			
5. <input type="checkbox"/> Incorporation By Reference (useable if Box 4b is checked) <input type="checkbox"/> The entire disclosure of the prior application, from which a copy of the oath or declaration is supplied under Box 4b, is considered to be part of the disclosure of the accompanying application and is hereby incorporated by reference therein			

JC530 U.S. PTO
09/590044

06/08/00

*NOTE FOR ITEMS 1 & 14: IN ORDER TO BE ENTITLED TO PAY SMALL ENTITY FEES, A SMALL ENTITY STATEMENT IS REQUIRED (37 C. F. R. § 1.27), EXCEPT IF ONE FILED IN A PRIOR APPLICATION IS RELIED UPON (37 C. F. R. § 1.28).

17. If a CONTINUING APPLICATION, check appropriate box and supply the requisite information below and in a preliminary amendment.
☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) of prior application No.: /
Prior application Information: Examiner Group/Art Unit:

18. CORRESPONDENCE ADDRESS
☐ Customer Number or Bar Code Label ☒ Correspondence address below
(Insert Customer No. or Attach bar code label here)

Name	Steven J. Frank				
Address	Cesari and McKenna 30 Rowes Wharf				
City	Boston	State	MA	Zip Code	02110
Country	U. S. A.	Telephone	(617) 951-2500	Fax	(617) 951-3927

Name (Print/Type)	Michael R. Reinemann	Registration No. (Attorney/Agent)	38,280
Signature	<i>Michael R. Reinemann</i>	Date	June 8, 2000

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In Re The Application of:)
Joseph M. Jacobson et al.)
Serial No.: 60/138,332) Examiner: Not Yet Assigned
Filed: June 9, 1999) Art Unit: Not Yet Assigned
For: METHODS AND APPARATUS)
FOR MANUFACTURING BIOE-)
LECTRONIC DEVICES)
Cesari and McKenna, LLP
30 Rowes Wharf
Boston, MA 02110
June 8, 2000

EXPRESS-MAIL DEPOSIT

“Express Mail” Mailing-Label Number: EL056745053US

The following papers are being deposited with the United States Postal Service
“Express Mail Post Office to Addressee” service pursuant to 37 C.F.R. §1.10:

X Patent Application (24 pages including 30 claims)
X Oath or Declaration (unsigned) X Informal Drawing (4 sheets)
X Check No. for \$948.00 X Fee Transmittal

METHODS AND APPARATUS FOR MANUFACTURING BIOELECTRONIC DEVICES

METHODS AND APPARATUS FOR MANUFACTURING BIOELECTRONIC DEVICES

RELATED APPLICATION

5 This application stems from U.S. Provisional Application Serial No.
60/138,332, filed on June 9, 1999.

BACKGROUND OF THE INVENTION

Field of the Invention

10 The present invention relates to fabrication of electronic structures involv-
ing biological or biochemical components.

Background Information

Electronic and electromechanical components are presently fabricated in
large, industrial manufacturing facilities that are tremendously expensive to build
15 and operate. For example, semiconductor device fabrication generally requires

specialized microlithography and chemical etching equipment, as well as extensive measures to avoid process contamination.

5 The fabrication processes ordinarily employed to create electronic and electromechanical components are expensive and limited in the quantities, which they can produce. In addition they typically involve harsh conditions such as high temperatures and/or caustic chemicals. The ability to integrate the manufacture of such electronic and electromechanical components with biological and bioorganic molecules is becoming increasingly important. An example of this integration is the so-called "biochip," i.e., an electronically active or readable substrate
10 having a dense array of different biological materials (e.g., DNA probes). Such a chip can be used, for example, to identify samples of interest or to test for the presence of various molecular sequences. See, e.g., U.S. Patent Nos. 5,605,662, 5,874,219, and 5,837,832.

15 SUMMARY OF THE INVENTION

The present invention provides an alternative to traditional fabrication of electronic components that is economical, scalable and facilitates incorporation of delicate materials. In particular, the invention utilizes nanoparticles to create, through deposition and patterning, microelectronic devices that incorporate biological materials. As used herein, the term "biological material" means any bio-
20 logical, bio-organic, or organic material exhibiting biological activity or capable of

interacting with a biologically active material; examples of biological materials include, without limitation, proteins, polypeptides (ranging from small oligopeptides to large functional molecules), nucleic acids, polysaccharides, carbohydrates, enzyme substrates, antigens, antibodies, pharmaceuticals, etc.

5 In accordance with the invention, one or more biological materials are associated, either by direct chemical bonding or by contact, with electrically active materials provided (at least initially) in the form of nanoparticles. In one aspect the invention exploits the fact that many physical, electrical, and optical properties that appear constant in the bulk of organic and inorganic materials are size-
10 dependent at the very small scales characteristic of nanoparticles. At these sizes—ranging from nearly 1 to 999 nm—the ratio of surface atoms to interior atoms becomes non-negligible, and particle properties therefore lie between those of the bulk and atomic materials. Monodisperse (i.e., uniformly sized) or polydisperse nanoparticles can form stable colloids in appropriate dispersing media, facilitating their deposition and processing in a liquid state. As a result printing
15 technology can be utilized to deposit and pattern nanoparticles.

 Furthermore, a key property that changes at small sizes is melting point. The effect is substantial; in some semiconductors, melting points have been observed to drop more than 1000 °C from the bulk material. The melting point depression observed in nanoparticle systems facilitates the low-temperature sintering, annealing, and melting of nanoparticles into crystalline films. As a result, nanoparticles can be printed and heated at low temperatures to form films of the
20

bulk material, in some cases without damage to associated biological materials, or can instead be printed and left in dispersed form to retain the size-dependent properties characteristic of the nanoparticles. Alternatively nanoparticles may be printed to form electronic, microelectromechanical or microfluidic devices and
5 then subsequently biological material may be printed or added to form a bioelectronic component.

Unlike conventional electrically active particles, nanoparticles are formed not by grinding, but instead via chemical methods (such as pyrolysis) or physical methods (such as physical vapor synthesis). Nanoparticles useful in accordance
10 with the present invention may be pristine or surrounded by a "capping" group to passivate the surface, alter surface chemistry, facilitate dispersion in a liquid, or, in many applications, to bind a biological material. Following their deposition, nanoparticles can self-assemble to form highly ordered thin films and superlattices that may exhibit multiple phases.

15 Accordingly, in a preferred embodiment, the invention comprises a method of fabricating a bioelectronic component. In accordance with the method, nanoparticles are surrounded by attached shells of at least one biological material. The nanoparticles may then be deposited (e.g., using a printing process) onto a surface. By associating the deposited nanoparticles with one or more electrical
20 contacts, electrical measurement across the nanoparticles (and, consequently, across the biological material) may be made. The device may include a plurality of layers formed by nanoparticle deposition. The nanoparticles within each de-

posited layer may be immobilized (by fusing, melting, or annealing the particles into a continuous material, by curing the carrier into a permanent matrix, by surrounding the nanoparticles with bifunctional surface groups that link adjacent nanoparticles, or merely by evaporating the carrier using heat or low pressure) in order to facilitate performance of the intended function. Also within the scope of the invention are components fabricated in accordance with the methods hereof.

BRIEF DESCRIPTION OF THE DRAWINGS

The invention description below refers to the accompanying drawings, of which:

Fig. 1 is a greatly enlarged side elevation of a chemFET transistor device fabricated in accordance with the present invention;

Fig. 2 is a greatly enlarged side elevation of an alternative chem-FET transistor;

Fig. 3 is a greatly enlarged depiction of a SET transistor device fabricated in accordance with the present invention; and

Fig. 4 is a greatly enlarged microfluidics device fabricated in accordance with the present invention.

DETAILED DESCRIPTION OF AN ILLUSTRATIVE EMBODIMENT

1. Nanoparticle Synthesis and Suspension

Particles useful in accordance with the present invention may be mono-disperse or polydisperse, and may represent a homogeneous suspension of a single species of nanoparticle or a heterogeneous suspension of different nanoparticles. Representative classes of nanoparticle include insulators (e.g., silicon dioxide); semiconductors (e.g., silicon or cadmium selenide); and conductors (e.g., gold or silver).

Numerous synthetic approaches, including pyrolysis of organometallic precursors, arrested precipitation, precipitation in reverse micelles, and exchange (metathesis) reactions, have been used to generate nanoparticles. See, e.g., Alivisatos, "Electrical Studies of Semiconductor-Nanocrystal Colloids," *MRS Bulletin*, Feb. 1998, at 18-23. In principle, virtually any nanoparticle synthesis is appropriate for the production of nanoparticles for the purposes of the present invention. However, because nanoparticle properties depend strongly on size, shape, crystallinity, and surface derivatization, in practice the particle synthesis is tailored so as to control these parameters for a particular application. In general, if the nanoparticles are not intended for bulk thick or thin film deposition—i.e., they will be applied and utilized in their native particulate state without subsequent fusion into the bulk material—then any synthesis yielding appropriate size control and crystallinity can be utilized.

On the other hand, if the particles are printed as a precursor to bulk thick or thin films, the synthesis should yield particles without tightly bound or heavy capping groups. Capping groups (sometimes used during synthesis to retard particle growth) can be problematic in bulk film applications if they become

5 trapped as impurities or impede crystal growth, thereby compromising film quality. Pyrolytic syntheses using pyridines and other coordinating solvents (see, e.g., Murray et al., *J. Am. Chem. Soc.* **115**:8706 (1993)), micelle-based approaches (see, e.g., Steigerwald et al., *J. Am. Chem. Soc.* **110**:3046 (1988)), and some metathetic preparations (see, e.g., Jarvis et al., *Mat. Res. Soc. Symp. Proc.* **272**:229 (1992)) can all yield particles free of heavy organic capping

10 groups. U.S. Application Serial No. 09/334,873, filed on June 17, 1999 and hereby incorporated by reference, discloses techniques of metathesis synthesis to form very small particles without the use of heavy capping groups.

Although in some circumstances it is possible to attach biological materials directly to a nanoparticle, attachment is more generally facilitated by surrounding the nanoparticles with an organic capping group, which envelopes the typically inorganic particle core as a shell capable of binding to biological molecules of interest. For example, silicon nanoparticles can be coated with 3-aminopropyltriethoxysilane (present, for example, as a 5% aqueous solution in

15 which the nanoparticles are dispersed). Single-stranded DNA may then be coupled to the coated nanoparticles using the well-known *N*-bromosuccinimide method (see Keller et al., *Anal. Biochem.* **170**:441 (1988)). As an alternative example, proteins may be conveniently linked to gold nanoparticles by a chemical

20

linkage of said gold nanoparticle to a cysteine amino acid group either naturally present in the protein or engineered to be present in the protein.

Additionally, the capping groups can act as a critical component in a device. For example, the caps (including attached biomolecules) can act as electrical insulators or sensitizers.

Nanoparticles are known to self-assemble into ordered arrays and superlattices, both with and without capping groups. If such ordered films orient not only particles but also their crystal planes, then long-range crystal order may be expected upon sintering, annealing, or melting. Highly faceted particles may be more likely to align their crystal planes than unfaceted particles. Self-assembly also offers the possibility of printing multiple phases or layers in a single pass, or for printing some pre-assembled structures or structures that assemble during the printing. Thus, different layers or regions might form as a result of a single printing step. Layers may form by size affinity, with large and small particles tending to group with other particles of similar size. See, e.g., Heath et al., *J. Phys. Chem. B* **101**:189 (1997) and Dabbousi et al., *Chem. of Mat'ls.* **6**:216 (1994), showing size-based particle clustering. Three-dimensional structures have been observed to occur when particles of different sizes are brought together and small particles cluster around single large ones.

2. Applications

Nanoparticles suspended in a liquid can be deposited and patterned onto a substrate using any of a wide variety of processes, including ink jetting, spin-coating, casting, lithography, gravure printing, screen printing, impact printing, stamping, embossing, contact printing (whereby a liquid or solid pattern is transferred from a plate, stamp or cylinder), or transfer onto the substrate through a mask. Moreover, nanoparticles may be applied in the dry state by dry jetting, laser printing or electrophotography (whereby a substrate receives a charge pattern and the particles are drawn to the charged regions). Deposition or application may generally occur in an uncontrolled atmospheric environment, but a controlled atmosphere generally provides better process control. The deposited layers may serve as conductive, semiconductive, or insulating layers, chemically or biologically active layers, or as etch resists, light barriers, diffusion barriers, passivation layers, adhesion layers, encapsulants, or structural supports.

A representative application of the present invention is fabrication of chem-FETs. In a traditional field-effect transistor, the electrical resistance of the current path between source and drain elements is varied by applying a voltage to the gate element, which is separated from source and drain by a dielectric. In a chemFET, the metal gate element is removed, and the dielectric used as a sensor surface. When charged species such as polar molecules or ions bind to the dielectric, the source-drain conductivity is altered, and this change can be detected and measured through operation of the device. Accordingly, by appro-

5

10

15

20

prove selected electrical and/or mechanical properties. To anneal the particles, the temperature of the environment is elevated to a point high enough to remove the capping groups (if any) and to cause fusion, annealing, or melting of particles in all layers for which a bulk film is desired. Alternatively, electromagnetic radiation, such as from a heat lamp or laser, may be used to thermally convert the nanoparticles to their bulk state.

This configuration facilitates the detection of specific biological materials 130 disposed on layer 125. In the case of oligonucleotides, for example, hybridization with complementary nucleic-acid strands can be detected. Layer 125 may be configured for interaction with biological material 130 in any of various ways. In one approach, layer 125 is an insulator film fabricated by sintering a deposited nanoparticle colloid and subsequently treating the material to expose reactive hydroxyl groups that bind with the biological material. In one instance such biological material may be disposed on the insulator by means of printing or micro-spotting the biological material onto the appropriate location. Alternatively they may be self assembled by means of specific chemical interactions with layer 125 or electrostatically assembled by applying a potential to the device electrodes. In certain cases dielectric layer 125 may be obviated and biological material 130 attached directly to semiconducting layer 110.

The transistor illustrated in FIG. 1 may be connected to other printed or non-printed components to form functional electronic circuits. The means of connection may, for example, be established by deposition of nanoparticle con-

ductors and, if necessary, insulators. These circuits may be connected to other printed or non-printed electronic, mechanical, chemical, or electromechanical devices.

Alternatively, a dielectric layer can consist of unsintered nanoparticles.

5 These may either be insulating nanoparticles or beads with attached biological material. Alternatively they may be conducting or semiconducting and will collectively act as an insulator due to retention of the capping group, which thereby provides sites for chemical modification (so that the biological material reacts with the cap, or a material subsequently bound to the cap, rather than with the inorganic nanoparticle material). Referring to Figure 2, a chemFET 200 comprises a semiconductor layer 210, a source element 215s, and a drain element 215d. These constituents may be fabricated as discussed above, i.e., by deposition and sintering of nanoparticles having appropriate conductivities. A layer 220 of nanoparticles having a biological material of interest attached thereto is applied onto semiconductor layer 210 between source and drain elements 215d, 215s. Such nanoparticles with attached biological material would generally be insulating nanoparticles or beads with directly bound biological material. Alternatively they could be conducting or semiconducting nanoparticles with appropriate capping groups. Such biological material may be positioned appropriately in one instance by means of printing or microspotting the biological material. Alternatively said biological material be self assembled by means of specific chemical interaction or electrostatically assembled by applying a potential to the device electrodes.

10

15

20

The contacts may, for example, be synthesized carbon nanotubes with modified chemical ends such that the nanoparticle self assembles onto them. Alternatively electrodes may be formed by printing conductive nanoparticles or by conventional photolithographic or other means and then employing electromigration, electroplating or electrofusing under feedback control to realize the nanoscale electrode spacing required for single electron transistor operation. Thus formed, contacts 315, 317 are exposed to a solution of nanoparticles having capping groups and, radiating therefrom (typically as a tangle of minute threads), biomolecules of interest. The interelectrode spacing distance approximates the size of the nanoparticles, so that a single nanoparticle can lodge between the electrodes and bridge them. Reagents affecting the biological material may be directly adsorbed onto (or absorbed into) the nanoparticle, and the effect monitored by operation of the device.

As described, a SET typically consists of a single nanoparticle disposed between two nanoelectrodes and insulated from those nanoelectrodes by means of insulating capping groups. An alternative arrangement consists of a chain of nanoparticles between electrodes insulated from each other and from the electrodes by means of insulating capping groups. Such a chain may be formed by applying an electric field to the electrodes in the presence of a solution of nanoparticles. Conduction is by means of electron hopping. If the nanoparticles have associated with them biological material, then the hopping probability and thus the current flow is affected by other molecules interacting with the associated biological material and may be measured.

In addition to chemFETs and SETs, electrometers for sensing charged material can also be fabricated using a technology known as light-addressable potentiometer systems (LAPs) or single point potential (SPP) electrometers. The principle is nearly identical to that underlying chemFETs except that only one
5 electrode per device is required. These devices, too, can be printed with nano-particle technology.

For biochips, many reactions are analyzed in parallel, requiring arrays of integrated sensors. Devices such as chemFETs, SETs, or SPPs can be printed in arrays where rows and columns are isolated from each other (as described, for
10 example, in copending application Serial No. 08/820,057, filed on March 18, 1997 and entitled PRINTABLE ELECTRONIC DISPLAY). A memory circuit can also be constructed using printed SETs in accordance with copending application Serial No. 09/291,801, filed on April 14, 1999 and entitled MEMORY
STRUCTURES AND METHODS OF MAKING SAME. The entire disclosures of
15 both of these applications are hereby incorporated by reference.

In another application of SET technology, a polymerase molecule (generally bound to a nanoparticle) is suspended between SET electrodes. Nucleic-acid polymerases are enzymes that catalyze synthesis of a nucleic-acid chain based on a template. In the presence of appropriate nucleosides, a polymerase
20 follows the template (which may be single- or double-stranded DNA, or RNA) and causes synthesis of its complement. In accordance with one aspect of the present invention, the applied field is used to sense the conformational change of the

enzyme during synthesis, thereby revealing the sequence of the template strand (as well as the synthesized strand). That is, the electrical signal produced by the SET during the course of synthesis encodes the identity of the template and synthesized strands, since the conformational changes—and the corresponding
5 effects on current flow through the SET—of the polymerase are characteristic for particular bases.

In a related aspect, the synthetic action of the polymerase is directed rather than merely observed. The polymerase enzyme functions by means of a catalytic reaction crevice whose conformational attributes are altered slightly by
10 interaction with a nucleotide base from the template. Using one or more nano-electrode or STM tips applied to the polymerase, the molecule can be caused to selectively assume conformational changes, which will induce 'errors' in the copy of a homopolymer template. Such 'errors' may encode data either as memory or to be fed into another polymerase attached to a SET readout. Such a system
15 thus realizes the basic components of a read and write memory system.

Figure 4 illustrates an electrically controllable microfluidic. In this case, a linear drive motor 400, which is useful for transporting biological molecules which may be bound to nanoparticles or beads 430 for the purpose of carrying out chemistry and transport. The device is created by printing conducting nanoparti-
20 cles to form the three phases 401, 402 and 403 of three phase linear drive motor. In addition walls or fluidic channels may be printed for containment of a fluid media.

5

17

CLAIMS

- 1 1. A method of fabricating a bioelectronic component, the method comprising
2 the steps of:
- 3 a. providing a batch of nanoparticles having submicron sizes and a se-
4 lected electrical characteristic;
- 5 b. attaching at least one biological material to the nanoparticles so as to
6 form shells of the biological material therearound;
- 7 c. depositing the nanoparticles onto a surface; and
- 8 d. associating the deposited nanoparticles with at least one electrical
9 contact to facilitate an electrical measurement thereof, the electrical
10 measurement being affected by the biological material.
- 1 2. The method of claim 1 in which the nanoparticles associate with said
2 electrical contact by means of self-assembly.
- 1 3. The method of claim 1 in which the nanoparticles associate with said
2 electrical contact by means of electrostatic assembly.
- 1 4. The method of claim 1 wherein the nanoparticles are semiconductive.
- 1 5. The method of claim 1 wherein the nanoparticles are conductive.

- 1 6. The method of claim 1 wherein the nanoparticles, surrounded by the bio-
2 logical material, collectively act as an insulator.
- 1 7. The method of claim 1 wherein the component is a transistor.
- 1 8. The method of claim 1 repeated at a plurality of locations on a substrate to
2 form an array of bioelectronic components.
- 1 9. The method of claim 1 further comprising the steps of:
2 e. providing a second batch of nanoparticles having submicron sizes and
3 a selected electrical characteristic;
4 f. depositing the second-batch nanoparticles onto a surface; and
5 g. sintering the second-batch nanoparticles to form a continuous, uniform
6 layer exhibiting the second-batch selected electrical characteristic, the layer
7 having a surface, the nanoparticles surrounded by the biological material being
8 deposited onto the layer surface.
- 1 10. The method of claim 9 further comprising the step of forming the electrical
2 contacts according to steps comprising:
3 h. providing a third batch of electrically conductive nanoparticles having
4 submicron sizes;
5 i. depositing the third-batch nanoparticles in contact with the layer derived
6 from the second-batch nanoparticles; and

1 11. The method of claim 10 further comprising the steps of repeating steps
2 (a)-(j) at a plurality of locations on a substrate to form an array of bioelectronic
3 components.

1 13. The method of claim 1 wherein the biological material comprises at least
2 one protein.

- a. providing a batch of nanoparticles having submicron sizes and a selected electrical characteristic;
- b. attaching at least one biological material to the nanoparticles so as to form shells of the biological material therearound, the surrounded nanoparticles having an average size;
- c. providing a pair of electrical contacts spaced apart to accommodate one or more nanoparticles; and

10 d. causing one or more surrounded nanoparticles to be disposed between
11 and bridge the contacts.

1 15. The method of claim 14 in which said nanoparticle disposed between
2 electrodes is realized by self-assembly.

1 16. The method of claim 14 in which said nanoparticle disposed between
2 electrodes is realized by electrostatic assembly.

1 17. The method of claim 14 wherein the component is a single-electron tran-
2 sistor.

1 18. The method of claim 14 repeated at a plurality of locations on a substrate
2 to form an array of bioelectronic components.

1 19. The method of claim 14 wherein the device is formed according to steps
2 comprising:

- 3 a. providing a batch of electrically conductive nanoparticles dispersed in a
4 carrier medium and having submicron sizes; and
5 b. applying an electric field to the dispersion so as to form a chain of
6 nanoparticles.

1 25. The method of claim 24 repeated at a plurality of locations on a substrate
2 to form an array of bioelectronic components.

- 1 26. A method of fabricating a bioelectronic component, the method comprising
2 the steps of:
3 a. providing a batch of nanoparticles having submicron sizes and a se-
4 lected electrical characteristic;
5 b. depositing the nanoparticles onto a surface;
6 c. sintering the batch of nanoparticles to form at least one layer of an
7 electrical device; and
8 d. associating a biological material with at least one layer of said electrical
9 device to facilitate an electrical measurement thereof, the electrical
10 measurement being affected by the biological material.
- 1 27. The method of claim 26 repeated at a plurality of locations on a substrate
2 to form an array of bioelectronic component.
- 1 28. The method of claim 26 in which said electrical device is a transistor.
- 1 29. The method of claim 26 in which said electrical device is a microelectro-
2 mechanical device.
- 1 30. The method of claim 26 in which said device is a microfluidic device.

24




FIGURE 1

008090"44006560




FIGURE 2

0050044-050800




FIGURE 3

000000-000000




FIGURE 4

008050-4400560

DECLARATION AND POWER OF ATTORNEY FOR PATENT APPLICATION

As a below-named inventor, I hereby declare that:

My residence, post-office address, and citizenship are as stated below next to my name.

I believe I am an original, first, and joint inventor of the subject matter which is claimed and for which a patent is sought on the invention entitled METHODS AND APPARATUS FOR MANUFACTURING BIOELECTRONIC DEVICES, the specification of which is attached hereto and identified by Cesari and McKenna File No. 109026-0068.

I hereby state that I have reviewed and understand the contents of the above-identified application specification, including the claims, as amended by any amendment specifically referred to herein.

I acknowledge the duty to disclose all information known to me that is material to patentability in accordance with Title 37, Code of Federal Regulations, §1.56.

I hereby claim foreign priority benefits under Title 35, United States Code §119(a)-(d) of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate filed by me on the same subject matter having a filing date before that of the application on which priority is claimed: None

I hereby claim the benefit under Title 35, United States Code §119(e) of the following U.S. provisional application: 60/138,332, filed June 9, 1999

I hereby claim the benefit under Title 35, United States Code §120, of the United States Application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United State Code, §112, I acknowledge the duty to disclose all information that is material to patentability in accordance with Title 37, Code of Federal Regulations, §1.56, and which became available to me between the filing date of the prior application and the national or PCT international filing date of this application: None.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment or both under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

I hereby appoint Michael E. Attaya, Reg. No. 31,731; Charles J. Barbas, Reg. No. 32,959; Joseph H. Born, Reg. No. 28,283; John L. Capone, Reg. No. 41,656; Robert A. Cesari, Reg. No. 18,381; Yong S. Choi, Reg. No. 43,324; Brian C. Dauphin, Reg. No. 40,983; Steven J. Frank, Reg. No. 33,497; Christopher K. Gagne, Reg. No. 36,142; A. Sidney Johnston, Reg. No. 29,548; William A. Loginov, Reg. No. 34,863; John F. McKenna, Reg. No. 20,912; Rama B. Nath, Reg. No. 27,072; Martin J. O'Donnell, Reg. No. 24,204; Thomas C. O'Konski, Reg. No. 26,320; Edwin H. Paul, Reg. No. 31,405; Michael R. Reinemann, Reg. No. 38,280; Rita M. Rooney, Reg. No. 30,585; Heather B. Shapiro, Reg. No. 41,305; Patricia A. Sheehan, Reg. No. 32,301; and Joseph Stecewycz, Reg. No. 34,442, Cesari and McKenna, LLP, 30 Rowes Wharf, Boston, Mass. 02110, jointly, and each of them severally, my attorneys and attorney, with full power of substitution, delegation and revocation, to prosecute this application, to make alterations and amendments therein, to receive the patent and to transact all business in the Patent and Trademark Office connected therewith. Please direct all telephone calls to Michael R. Reinemann at (617) 951-2500. Please address all correspondence to Michael R. Reinemann.

<u>Joseph M. Jacobson</u>	<u>Date</u>
Residence:	223 Grant Avenue Newton, MA 02159
Citizenship	U.S.A.
Post Office Address:	Same as above

<u>Scott Manalis</u>	<u>Date</u>
Residence:	100 Memorial Drive Cambridge, MA 02139
Citizenship	U.S.A.
Post Office Address:	Same as above

<u>Brent Ridley</u>	<u>Date</u>
Residence:	Eastgate #20B 60 Wadsworth Street Cambridge, MA 02142
Citizenship	U.S.A.
Post Office Address:	Same as above

008090"44005560